

128955-2

IN THE CLAIMS

1. (Currently amended) A resin composition ~~comprising~~ consisting essentially of: (A) 10 to 70 parts by weight polyphenylene ether, (B) 15 to 75 parts by weight syndiotactic polystyrene polymer, (C) 0 to 50 parts by weight atactic polystyrene resin, and (D) 5 to 40 parts by weight non-halogen fire retardant[[:]] wherein the sum of components (A)+(B)+(C)+(D) = 100 parts by weight, and (E) thermoplastic elastomer in an amount of 10 to 200 parts by weight to 100 parts by weight wherein the thermoplastic elastomer has a molecular weight distribution below 10 and the composition has a tensile strength greater than or equal to 34 and a tensile elongation greater than 5 when determined according to ASTM D638.
2. (Canceled)
3. (Original) The resin composition of Claim 1, wherein the polyphenylene ether component is poly(2,6-dimethyl-1,4-phenylene)ether having intrinsic viscosity in the range of 0.08 to 0.60 dl/g when measured in chloroform at 30°C.
4. (Currently amended) The resin composition of Claim 1, wherein the non-halogen fire retardant is an aromatic phosphoric ester.
5. (Currently amended) The resin composition of Claim 2, the wherein thermoplastic elastomer is a block copolymer of styrene and butadiene or styrene and isoprene.
6. (Original) A wire covering made from the resin composition of Claim 1.
7. (Original) A cable covering made from the resin composition of Claim 1